

TEST REPORT

Wistar Enterprises Limited

Room 1202, Block A, Sea View Estate, Watson Road 2-8, North Point, Hong Kong. Report No.: A42010768

Project No.: --Date: Dec 19, 2007

Page 1 of 3

Attn.: Carl / Janice

SAMPLE DESCRIPTION

: Tarpaulin PVC 500D x 500D x 18T x 17T thickness 0.6mm

ITEM NO.

: CM 3350/1

SKU NO.

: Not Provided

P.O. NO.

: Not Provided

EXPORTED TO

: Not Provided

COUNTRY OF ORIGIN

: Not Provided

DATE RECEIVED SAMPLES

: Dec 10, 2007

DATE OF TEST

: Dec 10 - 18, 2007

TEST REQUESTED

: Examination and test for compliance with appropriate tests of:

a. Modified EN 1021-1: 2006

RESULTS

Please refer to the following pages.

CONCLUSION:

Modified EN 1021-1: 2006

Pass(see remark 5)

Note: The results relate only to the items tested.

For and on behalf of SPECIALIZED TECHNOLOGY RESOURCES (H.K.) LTD.

Terence Chow

Technical Manager - Hardlines

Andar .

This report and / or certificate shall not be reproduced (except in full version) without the written approval of the Specialized Technology Resources (H.K.) Ltd. ("STR")



TEST REPORT

Wistar Enterprises Limited

Room 1202, Block A, Sea View Estate, Watson Road 2-8, North Point, Hong Kong. Report No.: A42010768

Project No.: --Date: Dec 19, 2007

Page 2 of 3

TEST RESULTS

A. Modified EN 1021-1: 2006, Furniture – Assessment of the Ignitability of Upholstery Furniture #

Sample: Tarpaulin PVC

Test method: EN 1021-1: 2006 (Smouldering cigarette)

Condition of test specimen: Temperature $23 \pm 2^{\circ}$ C Relative Humidity $50 \pm 5\%$

Test Condition: Temperature 23°C Relative Humidity 54%

Criteria of ignition		Smouldering cigarette	
		1	2
Sm	ouldering Criteria (EN 1021-1:2006, Section 3.1)		
a.	Any test assembly that displays escalating combustion behavior so that it is unsafe to continue the test and extinction is necessary	No	No
b.	Any test assembly that until it is largely consumed within the test duration	No	No
C.	Any test assembly that smouldering to the extremities of the specimen, vix. Upper or lower margins, either side or to its full thickness, within the duration of the tests	No	No
d.	Any test assembly that smouldering after one more hour from he beginning of the test.	No	No
e.	Any test assembly that on final examination, shows evidence of active smouldering	No	No
Fla	ming criteria (EN 1021-1:2006, Section 3.2)		
a.	Any flamer initiated by a smouldering source.	No	No
Result		Non-ignition	

#The test was performed by sub-contractor.

Remarks:

- The above test results relate only to the ignitability of the submitted sample with specific material, construction amd treatment under the particular conditions of test.
- The above test results are not intended as a means of assessing the full potential fire hazard of the materials or products in use.
- Water soaking procedure was carried out on cover material in accordance with Annex D of EN 1021-1:2006
- 4) °C denotes degree Celsius
 - % denotes percentage
- No filling/foam were submitted for the testing, the submitted sample(Tarpaulin PVC cover) was tested in combination with non-fire retardant foam provided by the laboratory per client's request.

This report and / or certificate shall not be reproduced (except in full version) without the written approval of the Specialized Technology Resources (H.K.) Ltd. ("STR")



TEST REPORT


Wistar Enterprises Limited

Room 1202, Block A, Sea View Estate, Watson Road 2-8, North Point, Hong Kong. Report No.: A42010768

Project No.: --Date: Dec 19, 2007

Page 3 of 3

PRODUCT PHOTO:



SAMPLES RECEIVED RECORD:

Receive Date	Sample Type	Quantity
12/10/2007	PVC	1 Pc

This report and / or certificate shall not be reproduced (except in full version) without the written approval of the Specialized Technology Resources (H.K.) Ltd. ("STR")